

**Listing of the Claims:**

Claims 1-20 (canceled).

21. (currently amended) A memory cell intermediate structure, comprising:

- a substrate;
- a first conductor formed on said substrate;
- an insulator formed on said first conductor, at least one via formed within said insulator and extending to said first conductor;
- a metallic material formed in said at least one via; and
- a flowable oxide material localized only within said via and over said metallic material within said via, wherein a portion of a sidewall region of said via is exposed.

22. (Previously presented) The memory cell intermediate structure of claim 21, wherein said metallic material comprises silver.

23. (cancelled)

24. (Previously presented) The memory cell intermediate structure of claim 21, wherein said metallic material is deposited on a surface of said insulator.

25. (currently amended) A programmable conductor random access memory intermediate structure, comprising:

a metallic material formed on a surface of an insulating layer and within and over a bottom of a via in said insulating layer; and

a flowable oxide material localized only within said via and over said metallic material within said via, wherein a portion of a sidewall region of said via is exposed.

26. (Previously presented) The programmable conductor random access memory intermediate structure of claim 25, wherein said metallic material comprises silver.

27. (cancelled)

28. (Previously presented) The programmable conductor random access memory intermediate structure of claim 25, wherein said flowable oxide comprises silicon oxide.

29. (Previously presented) The programmable conductor random access memory intermediate structure of claim 28, wherein said silicon oxide is in a flowable form in a temperature range of 50° C to 90° C.